




scandinaviannonwoven

Technical Data Sheet

Needlefelt 150 g/m²



Product code: Needlefelt OPAN 150 g/m²
Composition: 100% OPAN
Color: Black

Parameter	Unit	Test method	Average Value
Basis weight	g/m ²	ISO 9073-1	150 ± 5%
Thickness	mm	ISO 9073-2	1,5 ± 10%
Tensile strength (MD)	N/5 cm	ISO 9073-3	>100
Tensile strength (CD)	N/5 cm	ISO 9073-3	>100
LOI	l/dm ² /min	ASTM D2863	35 ± 2
Heat resistance @ 260°C			
Shrinkage (MD)	%	ISO 17493	≤3
Shrinkage (CD)	%	ISO 17493	≤3
Vertical Flame Test	Sec	ASTM D 6413	After Flame time - ≤ 2 sec After Glow time - ≤ 2 sec Char length time - ≤ 50 mm

This is not a specification. Properties are given as typical values.